

# BAM Bundesanstalt für Materialforschung und -prüfung

in co-operation with the Committee of Chemists of the GDMB  
Gesellschaft der Metallurgen und Bergleute e.V.

## Certified Reference Material

### BAM-M384b Pure Copper

#### Certified Values

Element	Mass fraction <sup>1)</sup> in mg/kg	Uncertainty <sup>2)</sup> in mg/kg
Ag	11.3	0.4
As	6.6	1.1
Bi	6.81	0.23
Cd	4.0	0.2
Co	10.4	0.5
Mg	3.3	0.5
Mn	8.1	0.9
Ni	4.7	0.6
Pb	1.6	0.4
Sb	5.8	0.4
Sn	2.1	0.4
Te	7.2	0.7
Ti	2.9	0.6
Zn	2.6	0.5
Zr	1.3	0.4

<sup>1)</sup> Unweighted mean value of the means of accepted sets of data (consisting of at least 3 but usually 6 single results), each set being obtained by a different laboratory and/or a different method of measurement. The values are traceable to the SI (Système International d'Unités) via calibration using pure metals or substances of known stoichiometry.

<sup>2)</sup> Estimated expanded uncertainty *U* with a coverage factor of *k*=2, corresponding to a level of confidence of approx. 95 %, as defined in the Guide to the expression of uncertainty in measurement, (GUM, ISO/IEC Guide 98-3:2008).

#### Sample description

The Reference Material is available in the form of discs (38 mm diameter and 30 mm height).

## Indicative values

Element	Mass fraction <sup>1)</sup> in mg/kg	Uncertainty <sup>2)</sup> in mg/kg
Al	2.9	0.8
Cr	2.3	0.6
Fe	5.1	1.2
P	< 2	
S	3.8	1.4
Se	2.9	0.7
Si	< 2.5	

<sup>1)</sup> Values were not certified, but given as indicative values, when the number of accepted data sets was considered to be too low (< 5) or when the uncertainty from the inter-laboratory certification was considerably larger than the expected range. The values are traceable to the SI (Système International d'Unités) via calibration using pure metals or substances of known stoichiometry.

<sup>2)</sup> Estimated expanded uncertainty  $U$  with a coverage factor of  $k = 2$ , as defined in the Guide to the expression of uncertainty in measurement, (GUM, ISO/IEC Guide 98-3:2008).

## Informative Value

One laboratory determined oxygen and found 0.15 % mass fraction.

## Recommended Use

The CRM is intended for establishing or checking the calibration of optical emission and X-ray spectrometers for the analysis of samples of similar matrix composition. The minimum sample size for wet chemical analysis is 0.5 g.

## Instructions for Use

Before use, the surface of the material must be prepared by milling or turning on a lathe. For wet chemical analysis chips have to be prepared by turning or milling of the sample surface.

## Participating Laboratories

Allgemeine Gold- und Silberscheideanstalt, Pforzheim, Germany  
Aurubis AG, Hamburg, Germany  
BAM Bundesanstalt für Materialforschung und -prüfung, Berlin, Germany  
Codelco, Chuquicamata, Chile  
Diehl Metall Stiftung & Co KG, Röthenbach, Germany  
Institut Glörfeld, Willich, Germany  
Johannes Gutenberg-Universität Mainz, Institut für Kernchemie, Mainz, Germany  
Montanwerke Brixlegg, Brixlegg, Austria  
Outokumpu VDM, Werdohl, Germany  
Umicore Precious Metals., Hoboken, Belgium  
Wieland-Werke AG, Vöhringen, Germany

## Means of Accepted Data Sets

Mass fraction in mg/kg

Certified values

Indicative values

Line no.	Ag	As	Bi	Cd	Co	Mg	Mn	Ni	Pb	Sb	Sn	Te	Ti	Zn	Zr	Al	Cr	Fe	P	S	Se	Si
1	10.03	5.49	---	3.73	---	---	---	3.40	1.00	---	1.48	5.98	---	1.38	0.83	1.00	1.24	1.98	0.04	< 1	1.20	1.00
2	10.90	5.76	6.59	3.80	---	2.50	6.28	3.54	1.23	5.46	1.78	6.30	2.53	1.50	< 1	2.22	1.47	3.41	0.10	2.97	1.71	1.70
3	11.00	6.00	6.67	3.88	9.34	3.00	7.10	4.16	1.37	5.50	1.88	6.44	2.68	1.75	< 1	2.80	1.65	4.38	0.15	3.79	2.47	3.17
4	11.06	6.05	6.69	3.89	9.60	3.15	7.25	4.50	1.44	5.57	2.03	6.48	2.82	1.80	1.00	2.83	1.71	4.48	< 1	4.53	2.67	3.95
5	11.18	6.60	6.75	3.93	9.87	3.18	7.64	4.65	1.55	5.68	2.17	7.50	2.84	2.41	1.23	2.88	< 2	4.50	< 1		2.87	
6	11.30	6.69	6.77	3.93	10.10	3.37	7.83	4.81	1.59	5.72	2.27	7.50	3.00	2.67	1.55	3.46	2.17	4.98	1.65		2.91	
7	11.43	7.00	6.84	3.99	10.58	3.54	8.50	4.95	1.67	5.75	2.28	7.55	3.32	2.91	1.57	3.83	2.87	5.05	1.68		3.31	
8	11.50	7.28	7.01	4.00	10.67	3.67	8.53	4.96	2.05	5.76	2.36	7.58	3.33	3.00	1.64	4.18	2.99	6.48			3.65	
9	11.53	7.30	7.20	4.15	10.83	3.95	8.95	4.97	2.14	6.00	2.50	7.74	---	3.02		3.07	7.45			4.25		
10	11.58	7.45	---	4.15	10.94		9.20	5.00	---	6.00		8.53		3.17		3.13	7.96			4.35		
11	11.72			---	11.20			9.86	5.18		6.04			3.31								
12	12.37				11.28				5.75		6.09											
13																						
$M$	11.30	6.56	6.81	4.00	10.44	3.29	8.11	4.66	1.56	5.78	2.08	7.16	2.93	2.55	1.30	2.90	2.18	5.07	< 2	3.76	2.94	1.95
$s_M$	0.56	0.71	0.21	0.14	0.68	0.45	1.09	0.68	0.37	0.23	0.33	0.81	0.31	0.66	0.34	1.00	0.78	1.81		0.79	1.02	1.11
$\bar{s}_i$	0.36	0.28	0.42	0.14	0.27	0.32	0.60	0.34	0.33	0.55	0.50	0.42	0.27	0.36	0.17	0.41	0.19	0.88		0.32	0.30	0.86

The laboratory mean values have been examined statistically to eliminate outlying values. Where a " --- " appears in the table it indicates that an outlying value has been omitted (Grubbs 95 %). A data set consists of at least 3 but usually 6 single values of one laboratory.

$M$  : mean of laboratory means

$s_M$  : standard deviation of laboratory means

$\bar{s}_i$  : averaged repeatability standard deviation (square root of the mean of laboratory variances)

Note: "< - values" were not included into the calculation of  $M$  and  $s_M$

## Analytical Method used for Certification

Element	Line no.	Method
Ag	1, 5	GD-MS
	2, 7	INAA
	3, 4, 8, 9, 10, 11, 12	ICP-OES
	6	ICP-MS
As	1, 2	GD-MS
	3, 5, 6, 8, 9, 10	ICP-OES
	4	ICP-MS
	7	ET AAS
Bi	2, 8	GD-MS
	3, 4	ET AAS
	5, 6, 9	ICP-OES
	7	ICP-MS
Cd	1, 2, 3, 4, 5, 7, 8, 9	ICP-OES
	6	ICP-MS
	10	GD-MS
Co	3, 4, 5, 6, 8, 12	ICP-OES
	7	INAA
	9, 10	GD-MS
	11	ICP-MS
Fe	1, 2, 3, 4, 5, 6, 7	ICP-OES
	8	GD-MS
	9	ICP-MS
	10	INAA
Mg	2, 3, 4, 6, 7, 8	ICP-OES
	5	GD-MS
	9	ICP-MS
Mn	2, 3, 4, 5, 6, 7, 11	ICP-OES
	8, 9	GD-MS
	10	ICP-MS
Ni	2	ET AAS
	3, 4, 5, 7, 9, 10, 11, 12	ICP-OES
	1, 6	GD-MS
	8	ICP-MS
Pb	1, 2, 8, 9	ICP-OES
	4, 7	ET AAS
	5	ICP-MS
	3, 6	GD-MS

<b>Element</b>	<b>Line no.</b>	<b>Method</b>
Sb	2, 3, 7, 9, 10 3, 4 5, 11 7 12	ICP-OES INAA GD-MS ICP-MS ET AAS
Sn	1, 7 2, 3, 4, 6, 8 5 9	GD-MS ICP-OES ICP-MS ET AAS
Te	1, 7 2, 4, 6 3 5 8, 9	GD-MS ICP-OES INAA ICP-MS ET AAS
Ti	2, 3, 5, 6, 8 4, 7	ICP-OES GD-MS
Zn	1, 3, 4, 5, 10, 11 2 6 7, 8 9	ICP-OES FAAS INAA GD-MS ICP-MS
Zr	1, 2, 3, 4, 8 5, 6 7	ICP-OES GD-MS ICP-MS
Al	1, 2, 3, 4, 5 6, 7 8	<i>ICP-OES</i> <i>GD-MS</i> <i>ICP-MS</i>
Cr	1, 2, 3, 4, 5, 6 7, 9 8 10	<i>ICP-OES</i> <i>GD-MS</i> <i>INAA</i> <i>ICP-MS</i>
P	1, 2 3 4, 5 6, 7	<i>GD-MS</i> <i>ETV-ICP-OES</i> <i>ICP-OES</i> <i>Spectrophotometry</i>
S	1, 3 2 4	<i>ICP-OES</i> <i>GD-MS</i> <i>Combustion/iodometric titration</i>
Se	1, 2, 3, 4, 9, 10 5 6, 8 7	<i>ICP-OES</i> <i>ET AAS</i> <i>GD-MS</i> <i>INAA</i>
Si	1, 3, 4 2	<i>ICP-OES</i> <i>GD-MS</i>

**Abbreviations:** ET AAS – Electrothermal atomic absorption spectrometry  
ETV-ICP-OES – Inductively coupled plasma - optical emission spectrometry plasma after electrothermal vaporisation  
FAAS – Flame atomic absorption spectrometry  
GD-MS – Glow discharge mass spectrometry  
ICP-MS – Mass spectrometry with inductively coupled plasma  
ICP-OES – Inductively coupled plasma - optical emission spectrometry  
INAA – Instrumental neutron activation analysis

## Transport and Storage

The material should be stored in a dry and clean environment at room temperature (approx. 20 °C). Transport under normal ambient conditions.

## Technical Report

A detailed technical report describing the analysis procedures and the treatment of the analytical data used to certify BAM-M384b is available on request or can be downloaded from BAM website ([www.bam.de/en/fachthemen/referenzmaterialien/index.htm](http://www.bam.de/en/fachthemen/referenzmaterialien/index.htm)).

**Accepted as BAM-CRM on 23-01-2014**

**BAM Bundesanstalt für Materialforschung und -prüfung**

Prof. Dr. U. Panne  
Head of Department 1  
Analytical Chemistry;  
Reference Materials

Dr. S. Recknagel  
Head of Division 1.6  
Inorganic Reference Materials

This Reference Material is offered by:

BAM Bundesanstalt für Materialforschung und -prüfung  
Richard-Willstätter-Str. 11, 12489 Berlin

Phone: +49 30 8104 2061  
Fax: +49 30 8104 1117

Email: [sales.crm@bam.de](mailto:sales.crm@bam.de)  
Internet: [www.webshop.bam.de](http://www.webshop.bam.de)